

Cite this: DOI: 10.1039/c0xx00000x

www.rsc.org/xxxxxx

Negative 2D thermal expansion in the halogen bonded acetone bromine complex.

W. G. Marshall^{a‡}, R. H. Jones^{b*} and, K. S. Knight^{c,d}.*Received (in XXX, XXX) Xth XXXXXXXXXX 20XX, Accepted Xth XXXXXXXXXX 20XX*

DOI: 10.1039/b000000x

The crystal structure of the complex formed between acetone and bromine has been determined between 14K and 200K. The structure exhibits negative 2D thermal expansion at low temperature and colossal thermal expansion in the perpendicular dimension. At low temperature the C=O bond is significantly longer than that observed in free acetone.

Most materials expand upon heating and for molecular solids values of the linear expansion coefficient comparable to that seen in ice 55 MK^{-1} (at 250 K)¹, are typical. When the value of the linear expansion coefficient is greater than 100 MK^{-1} such expansion is called colossal thermal expansion². Much rarer is the phenomena of negative thermal expansion (NTE) that occurs when a material contracts upon heating^{3,4}. It is possible for materials to exhibit both positive and negative thermal expansion in different directions⁵. Although rarer, NTE has been observed in a variety of materials such as zeolites⁶, metal oxides⁷, metal fluorides⁸, and cyanides^{9,10}, however in molecular solids NTE is much rarer¹¹⁻¹³. Recently we have shown that the halogen bonded complexes PyICl and PyIBr¹³ (py= pyridine) undergo colossal thermal expansion (147 and 176 MK^{-1}) coupled with negative thermal expansion in another direction.

We have previously determined the structure using neutron powder diffraction (110K) of one of the best-known halogen bonded complexes namely that between acetone and bromine¹⁴ which consists of chains of acetone and bromine molecules. Linking these molecules are strong halogen bonds between the acetone and bromine. Our results showed that the presence of a short intermolecular O---Br bond was accompanied by the elongation of the Br-Br bond, a result which had not been observed in an earlier study¹⁵. In addition to these changes, we observed small changes in bond length within the C=O groups, but not at a statistically significant level, whilst on a macroscopic level colossal thermal expansion was observed. Our objective in this study was to carry out an accurate low temperature study to obtain a more accurate value for the C=O bond length and a thermodiffraction study to investigate the thermal expansion of this material together with the structural changes that accompany heating.

The complex was prepared by mixing stoichiometric quantities of perdeuterioacetone and bromine at $0 \text{ }^\circ\text{C}$. The mixture was pipetted into a pre-cooled ($0 \text{ }^\circ\text{C}$) vanadium can fitted with a thin

walled quartz liner into which some amorphous quartz-glass wool had been placed. The vanadium can was sealed and cooled on a block of solid CO_2 prior to loading into a cryostat on the high resolution powder diffractometer at the ISIS facility. The sample was cooled to base temperature and 45 short data collections to obtain lattice parameters were made between 14 K and 200 K, in order to obtain information on the magnitudes and directions of the thermal expansion tensor. These short runs were interspersed with 4 longer runs. These longer runs were carried out with the intention to obtain accurate structural parameters in addition to the lattice parameters.

The use of neutrons as our radiation source has enabled us to obtain more accurate positions of the atoms with low atomic number in this complex and hence dimensions for the acetone molecule. This is because of the comparable magnitudes of the coherent scattering lengths of C, D, O and Br. This would not be the case, in an X-ray structure determination, where the structure factors would be dominated by the scattering from the bromine atoms.

Lattice parameters were obtained by using Model independent fits¹⁶, and the structural parameters were obtained by Rietveld refinement¹⁷. Selected interatomic contacts are given in Table 1, diagrams of the molecular structure are shown in Figure 1, difference Rietveld plots are available as supplementary material.

The structure at all temperatures is similar to that which we have previously described¹⁴, and there is good agreement for the Br-Br and O---Br distances with a recent theoretical study on this system¹⁸. In particular, there are two short O---Br interactions, for each acetone molecule, such that the bromine molecules are positioned towards the lone pairs of the oxygen atoms with a Br--O---Br angle of approximately 110° . All of these contacts are significantly shorter than the sum of the van der Waals radii of bromine and oxygen (3.45 \AA ¹⁹). These interactions result in syntactic chains being formed. These chains lie parallel to the (1 0 -1) plane giving rise to a sheet structure (Figure 2). It is to be noted that there are no strong intermolecular interactions between the chains that build up the layers of the sheet. In addition to these intermolecular interactions, there are also C-D---Br and C-D---O weak hydrogen bonds, the latter of which occur between the layers. At all temperatures the Br-Br bond lengths are longer than observed in either Br_2 vapour (2.28105 \AA ²⁰) or pure bromine in the solid state ($2.286(3) \text{ \AA}$ ²¹) with the difference being particularly pronounced at low temperature.

It should be noted that an earlier study on solid bromine showed that the bond length of the Br₂ molecules in the solid phase varies significantly as a function of temperature so that whilst at 5 K it is 2.301(2) Å (which is comparable to our 200K measurement), at 250K it is 2.286(3), this was accompanied by an increase in the intermolecular Br---Br contacts which expand from 3.286 Å (5 K). to 3.368 Å (250 K).




Figure 1 Structure illustrating Br---O and C-D---Br interactions Distances in Å




Figure 2 Plane of molecules (1 0 -1 plane)




Figure 3 View showing weak hydrogen bonds between layers

Table 1 Selected interatomic contacts/Å

Temp/K	C=O/Å	Br-Br/Å	O---Br/Å	Br---O---Br/°
14	1.248(4)	2.321(3)	2.737(2)	109.3(1)
35	1.243(3)	2.327(3)	2.734(2)	109.5(1)
75	1.250(4)	2.328(3)	2.737(2)	110.1(1)
110†	1.230(3)	2.322(2)	2.748(2)	110.5(1)
200	1.227(6)	2.309(5)	2.797(4)	110.1(2)

†¹⁴

A similar trend is observed in this study with short O---Br intermolecular contacts being accompanied by the greatest elongation of the Br – Br bond and occurring at low temperatures. For our lowest temperature measurements the C=O bond is significantly longer than seen in either our previous 110 K neutron structure 1.230(3)Å¹⁴, or the 200K structure (this work). The C=O bond length (110K) was at the longer end of the range of values reported for structures of acetone. For the purposes of comparison, the most pertinent of these were those given in a NPD structure refinement of pure deuterioacetone in which C=O bond lengths of 1.213(4) Å and 1.202(4) Å were determined for the two independent molecules in the asymmetric unit²².

We now turn to the thermal expansion properties of the material. Figures 4-7 show the variation of lattice parameters, and unit cell volume with temperature. From these graphs it can be clearly seen that both the a and b axis undergo negative thermal expansion at very low temp temperatures but positive thermal expansion at higher temperatures. Fitting a quadratic function of temperature over the range 14 – 75 K for both a and b give the point at which positive thermal expansion starts at 42K and 35K respectively. Whilst these plots are informative in establishing the occurrence of phenomena such as negative thermal expansion it has been pointed out that it is more useful to use the principal axes of the expansion tensor to extract information on the expansion properties²³. Consequently, We have analysed the lattice parameter data using the computer program PASCAL²⁴. Because of the occurrence of negative thermal expansion at low temperature we have analysed the data for two separate temperature ranges; the low temperature range 14 to 37 K, and the higher temperature range 47 to 200K. The thermal expansion coefficients and the normalised components of the principal axes projected onto the crystallographic axes, are given in Table 3, together with diagrams showing the thermal expansion for each of these temperatures regimes (Figure 8). Plots of material pertaining to the thermal expansion are available as supplementary information.

55

Table 2 Selected contacts involving deuterium

Temp/K	D6---Br1/Å	D7---Br1/Å	D5---O/Å
14	3.004(3)	3.017(3)	2.672(3)
35	2.994(3)	3.024(3)	2.666(2)
75	2.976(4)	3.049(3)	2.661(3)
110†	3.001(3)	3.060(4)	2.680(3)
200	2.986(7)	3.119(5)	2.777(5)

†¹⁵

Table 3

Temperature Regime 14 – 37 K

Axes	α MK ⁻¹	$\sigma\alpha$ MK ⁻¹	a	b	c
X ₁	-39.6	6.3	-0.9997	0	0.0244
X ₂	-18.2	6.0	0.0	1.0	0.0
X ₃	157.6	2.2	0.3617	0.0	0.935
V	109.6	12.9			

60

Temp Regime 47 200 K

Axes	α MK ⁻¹	$\sigma\alpha$ MK ⁻¹	a	b	c
X ₁	42.4	0.5	0.9733	0	0.2295
X ₂	67.3	2.1	0.0	-1.0	0.0
X ₃	169.3	3.3	-0.2682	0.0	0.9634
V	284.6	5.5			

One of the striking features of this material is the occurrence at low temperature of negative thermal expansion in two dimensions together with positive thermal expansion in the third. The larger of these contractions lies close to $[-1\ 0\ 0]$ and the smaller is along $[0\ 1\ 0]$. It has been pointed out that the occurrence of negative thermal expansion in two dimensions whilst accompanied by thermal expansion in the third giving rise to negative 2D expansion is itself quite rare^{23,24,25} and has only been seen in a limited number of materials²⁶⁻³⁰ for example MOF's²³ LiBeBO_3 ²⁵, Group 10 cyanides²⁶, graphite²⁷, the low temperature form of




Figure 4 Variation of $a/\text{Å}$ with T/K for $(\text{CD}_3)_2\text{CO-Br}_2$ Complex




Figure 5 Variation of $b/\text{Å}$ with T/K for $(\text{CD}_3)_2\text{CO-Br}_2$ Complex




Figure 6 Variation of $c/\text{Å}$ with T/K for $(\text{CD}_3)_2\text{CO-Br}_2$ Complex

arsenic²⁸, low temperature β 2,4-dinitroanisole²⁹, 1-ethyl-2,3-dimethylimidazolium bromide³⁰ and the lithium aluminosilicate, petalite³¹. In addition to the negative 2D expansion there is colossal expansion in the third direction. In the low temperature regime it can be seen that the colossal expansion occurs close to the $[1\ 0\ 3]$ direction. In order to more clearly formulate the factors responsible for this behaviour we have attempted to associate these macroscopic expansion properties with specific

intermolecular interactions.

At first sight (figure 2) it would appear that the bonds associated with expansion in the $[1\ 0\ 3]$ direction are the intermolecular O---Br bond, and intramolecular Br-Br bonds, together with the changes in the angle between 2 O---Br halogen bonds. However The 1-3 O---O distance has the same value 7.793 Å at 14 and 35 K.

We believe that the expansion correlates primarily at low temperatures with the reduction in the C4-D7---Br interactions, but the C4-D5---O hydrogen bond which also acts across the layers strengthen slightly. The net result is that adjacent chains




Figure 7 Variation of $V/\text{Å}^3$ with T/K for $(\text{CD}_3)_2\text{CO-Br}_2$ Complex




Figure 8 Expansivity Indicatrix for low(left) and high (right) temperature regions

move with respect to each other. This accompanied by the slight increase in the Br---O---Br angle which can be seen to expand as the temperature is raised (Table 1) At higher temperatures the C-D---O interaction also significantly weakens (Table 2) and is furthermore accompanied by weakening of the O---Br halogen bond (Table 1). These features are accompanied by increasing thermal motion of the methyl group further weakening these out of plane interactions and can be seen by the increase in thermal motion of methyl groups (supplementary data). At low temperatures there appears to be strengthening of the C-D---O interactions and it can be seen that there is a large component of this bond is parallel to a , this would suggest that negative expansion would result at the lowest temperature.

Finally it can be seen that the interaction C-D6---Br persists even at 200K. This interaction is situated within the layers, which explains its persistence, as increasing motion of the methyl

-
- Chippindale, E. J. Bilbé, E. Marelli, P. J. F. Harris and A. C. Hannon,
Inorg Chem, 2011, **50**, 104-113.
- 27 A. C. Bailey, and B. Yates, *B.J. Appl. Phys.* 1970 **41**, 5088.-5091.
- 28 R. W. Munn *J. Phys C*. 1972 **C5**, 535-542
- 5 29 H Takahashi and R Tamura *Crystengcomm* 2015, 17, 8888.-8896.
- 30 I de Pedro, A. Garcia-Saiz, J. DuPont, P. Migowski, A. Vallcorba, J.
Junquera, R. Ruis and J. Rodriguez-Fernandez *Crystal Growth and
Design* 2015, **15**, 5207-5212
- 31 K. S. Knight *J Miner Petrol Sci* 2014, **109**, 118-124.
- 10 32 F.J. Lovas and P Groner *J Mol Spec* 2006, **236**, 173-177
- 33 C. R. Groom, I. J. Bruno, M. P. Lightfoot and S. C. Ward *Acta Cryst.*
2016, **B72**, 171-179
- 34 G Zhang, W Wang, D Chen, *Chemical Physics*, 2009, **359**, 40-44.